

Original

Micro-computed tomographic analysis of progression of artificial enamel lesions in primary and permanent teeth after resin infiltration

Betul Memis Ozgul¹⁾, Kaan Orhan²⁾, and Firdevs Tulga Oz¹⁾

¹⁾Department of Pediatric Dentistry, Faculty of Dentistry, Ankara University, Ankara, Turkey

²⁾Department of Dentomaxillofacial Radiology, Faculty of Dentistry, Ankara University, Ankara, Turkey

(Received January 13, 2015; Accepted April 14, 2015)

Abstract: We investigated inhibition of lesion progression in artificial enamel lesions. Lesions were created on primary and permanent anterior teeth ($n = 10$ each) and were divided randomly into two groups with two windows: Group 1 (window A: resin infiltration; window B: negative control) and Group 2 (window A: resin infiltration + fluoride varnish; window B: fluoride varnish). After pH cycling, micro-computed tomography was used to analyze progression of lesion depth and changes in mineral density. Resin infiltration and resin infiltration + fluoride varnish significantly inhibited progression of lesion depth in primary teeth ($P < 0.05$). Inhibition of lesion depth progression in permanent teeth was significantly greater after treatment with resin infiltration + fluoride varnish than in the negative control ($P < 0.05$). Change in mineral density was smaller in the resin infiltration and resin infiltration + fluoride varnish groups; however, the difference was not significant for either group ($P > 0.05$). Resin infiltration is a promising method of inhibiting progression of caries lesions. (J Oral Sci 57, 177-183, 2015)

Keywords: fluoride; initial caries lesions; μ CT; resin infiltration.

Introduction

An ideal approach for treating non-cavitated enamel lesions—which are characterized by loss of minerals in the lesion body and comparatively high mineralization of the surface—is to maintain enamel integrity and minimize use of restorative treatment procedures (1). At an early stage, these lesions can be arrested or even remineralized by daily oral health procedures in patients with good oral hygiene (2,3). However, adherence to the required daily oral health procedures might be insufficient among children and adolescents.

For this reason, it has been suggested that infiltrating the existing lesion to prevent contact with oral fluids could arrest lesion progression (4,5). Recently, a new material, ICON (DMG, Hamburg, Germany), was developed to facilitate infiltration of low-viscosity resins into initial caries lesions. The effectiveness of this novel material has been tested *in vitro*. Several studies have investigated progression of artificial caries lesions using confocal microscopy and transversal microradiography (6,7). However, these methods require destructive sample preparation, and longitudinal analyses of the same lesion involve preparation of fragile single sections, which may be lost during the course of a study (8,9).

Micro-computed tomography (μ CT) is an innovative, noninvasive, and nondestructive approach for investigating the processes that occur in dental hard tissues (10). μ CT allows the use of the same specimens for several biological and mechanical tests (11,12). Additionally, μ CT facilitates evaluation of the quantity and quality of dental tissues, depth of caries lesions (13-15), and


Correspondence to Dr. Betül Memiş Özgül, Department of Pediatric Dentistry, Faculty of Dentistry, Ankara University, Besevler, Ankara, Turkey
E-mail: dtbetulmemis@hotmail.com

doi.org/10.2334/josnusd.57.177

DN/JST.JSTAGE/josnusd/57.177

Table 1 Composition of materials used in the study

Materials	Composition
Resin infiltrant ICON	TEGDMA-based resin matrix, initiator, additives
Fluoride varnish Duraphat	50 mg sodium fluoride, equivalent to 22.6 mg fluoride, in an alcohol solution of natural resins
Negative control physiologic serum	0.85% sodium chloride solution

**Fig. 1** Experimental set-up.

mineral loss in initial enamel caries lesions (11,16).

No study has used μ CT to evaluate inhibition of lesion progression with the resin infiltrant ICON. Thus, this study used μ CT to investigate inhibition of lesion progression in artificial primary and permanent enamel lesions after using resin infiltration, with and without fluoride varnish, and compares changes in lesion depth and mineral density associated with the use of fluoride varnish and physiologic serum.

Materials and Methods

The research protocol was approved by the Ethics Committee of the Ankara University Faculty of Dentistry in Ankara, Turkey (No: 19.10.2010-02/02). Oral and written informed consent was provided by the patients or parents/guardians of the patients.

Using data from previous μ CT studies (14,15), we conducted a power analysis (Power and Precision software, Biostat, Englewood, NJ, USA). The findings indicated a minimum sample size of $n = 5$, based on an α of 5% and a power of 80%.

Lesion formation

Ten extracted or naturally exfoliated primary anterior teeth (canines and maxillary incisors) and 10 permanent anterior teeth extracted for periodontal reasons were cleaned of soft tissue debris and inspected for cracks, hyperplasia, and white spot lesions under a stereomicroscope (Leica MZ12, Leica Microsystems,

Wetzlar, Germany). The 10 primary and permanent anterior teeth were then coated with an acid-resistant nail varnish (Maybelline, New York, NY, USA). Two narrow rectangular windows (approximately 4×2 mm) were left on the sound, intact buccal surface, and the teeth were embedded in paraffin blocks. The teeth were then immersed in demineralization solution (50 mL/tooth) for 96 h in a shaking incubator to produce lesions with a depth of 150-200 μ m. The demineralization solution used for creation of the initial lesions and during pH cycling contained 2.2 mM CaCl_2 , 2.2 mM NaH_2PO_4 , and 0.05 M acetic acid; pH was adjusted to 4.4 with 1 M KOH (17,18). After demineralization, each tooth had two initial enamel lesions (A, B), separated by nail varnish. The teeth were divided randomly into two equal groups ($n = 5$ each) and stored at 100% humidity until testing.

Test groups

For each tooth group, two windows were treated with different protocols. The compositions of the materials are shown in Table 1.

Group 1

Window A (resin infiltration): in accordance with the manufacturer's instructions, this window was etched with 15% HCl gel for 120 s, rinsed for 30 s, and dehydrated with 100% ethanol for 30 s. ICON (DMG, Hamburg, Germany) was applied with a microbrush for 3 min, excess material was gently removed with a small cotton pellet, and the resin was light-cured (Translux



Fig. 2 Reconstructed images of conical phantoms at 0.25 and 0.75 gHAp cm⁻³.




Fig. 3 (a) a 3D representation of the demineralized area, (b) a μ CT image of a specimen, including the surface and inner area of the enamel.

CL; Heraeus Kulzer, Hanau, Germany) for 40 s at 400 mW/cm². ICON was then applied a second time for an additional 1 min.

Window B (negative control): physiologic serum was applied with a microbrush.

Group 2

Window A (resin infiltration + fluoride varnish): ICON was applied as described above. After ICON application, a small amount of Duraphat (Colgate, Palmolive, Waltrop, Germany) was applied with a microbrush.

Window B (fluoride varnish): a small amount of Duraphat was applied with a microbrush. To evaluate progression in the infiltrated lesions, half of the specimens were covered with a nail varnish (Fig. 1). One half of each specimen was used to measure lesion depths and mineral density directly after infiltration (baseline). The remaining halves were exposed to pH cycling for 7 days to simulate a cariogenic environment (Demin; Fig. 1).

Demineralizing and remineralizing solutions

The demineralization solution used for creation of the initial lesions and during pH cycling contained 2.2 mM CaCl₂, 2.2 mM NaH₂PO₄, and 0.05 M acetic acid; pH was adjusted to 4.4 using 1 M KOH. The remineralizing solution contained 1.5 mM CaCl₂, 0.9 mM NaH₂PO₄, and 0.15 M KCl; pH was adjusted to 7.0. This solution simulated supersaturation of apatite minerals found in saliva and was similar to that used by Cate and Duijsters (17,19).

Model of pH cycling

The teeth underwent pH cycling in a shaking incubator for 7 days. Each cycle involved 3 h of demineralization twice per day with 2 h of remineralization in between. Sections were then placed in the remineralizing solution overnight. Fresh demineralizing and remineralizing solutions were prepared for each cycle, and separate containers were used for each group throughout the experimental period. Each demineralization and remineralizing session was followed by thorough rinsing with clean water.

μ CT evaluation

A high-resolution desktop μ CT system (Skyscan 1172, Skyscan, Kontich, Belgium) was used to scan the specimens. The scanning conditions were 1,000 kVp, 100-mA beam current, 0.5-mm Al/Cu filter, 13.74- μ m pixel size, rotation in 0.5° steps, and 40% beam hardening. To minimize ring artifacts, the detector was air-calibrated before each scan. Each sample was rotated 360° within an integration time of 5 min. The mean scanning time was about 2 h. Other settings included beam-hardening correction and input of optimal contrast limits (0-0.0005), based on data from prior scanning and tooth reconstruction.

μ CT image analysis

Nrecon software (ver. 1.6.7.2; Skyscan) and CtAn (ver. 1.12.9, Skyscan) were used for visualization and quantitative measurement of samples. A modified version of the algorithm described by Feldkamp et al. (20) was used to obtain axial 2-dimensional (2D) 1,000 \times 1,000-pixel images. For the reconstruction parameters, ring artefact correction and smoothing were fixed at zero, and beam artefact correction was set at 40%. The contrast limits were those specified in the SkyScan instructions. A similar procedure was used to measure the gray values of two bone mineral density (BMD) phantom rods. To aid mineral density (MD) calculations, grayscale values were converted into MD values (gHAp cm⁻³) with a linear calibration curve based on grayscale values obtained from two mineral concentration conical phantoms of 0.25 and 0.75 gHAp cm⁻³ (Fig. 2). Calculations of difference in mineral loss (ΔZ ; gHAp cm⁻³) for each specimen were made by calculating MD values from the entire demineralized area as the mean loss of surface and inner part of the demineralized area (Fig. 3). Mineral loss was calculated by subtracting demin MD values from baseline phantom rod MD values, to correct alignment inaccuracies from the specimen.

Lesion depth (LD) was calculated by subtracting the area of demineralization from the estimated area of sound

enamel before demineralization and pH cycling. For each tooth area, 3 calculations from 3 enamel levels were performed, and the mean value was used as the final LD. LD difference (Δ LD; μ m) was calculated by subtracting the demin LD values in each group from baseline LD values (Fig. 4).

Statistical comparisons

Differences in Δ LD and Δ Z between groups were examined with the Mann-Whitney *U* test. The Kruskal-Wallis




Fig. 4 Measurement of lesion depth.

H test with Bonferroni correction was used to determine the statistical significance of observed differences between groups. All analyses were performed using SPSS software (ver. 20; Chicago, IL, USA) at a significance level of $\alpha = 0.05$.

Results

Primary teeth

The differences in Δ Z among the four groups were not statistically significant ($P > 0.05$). Δ Z was 0.31 g/cm^3 for the negative control, 0.27 g/cm^3 for fluoride varnish, 0.14 g/cm^3 for resin infiltration, and 0.13 g/cm^3 for resin infiltration + fluoride varnish (Table 2).

There were statistically significant differences in Δ LD between groups. Progression of caries depth was significantly greater in the negative control and fluoride varnish groups than in the resin infiltration and resin infiltration + fluoride varnish groups ($P < 0.05$). Progression of caries depth was $64.4 \mu\text{m}$ in the negative control, $57.2 \mu\text{m}$ for fluoride varnish, $21 \mu\text{m}$ for resin infiltration, and $5.78 \mu\text{m}$ for resin infiltration + fluoride varnish (Table 2).

Permanent teeth

Differences in Δ Z between groups were not statistically significant ($P > 0.05$). Δ Z was 0.23 g/cm^3 for the negative control and fluoride varnish, 0.17 g/cm^3 for resin infiltration, and 0.14 g/cm^3 for resin infiltration + fluoride varnish (Table 2).

Progression of caries depth was $56.98 \mu\text{m}$ for the negative control, $54.8 \mu\text{m}$ for the fluoride varnish, $26.34 \mu\text{m}$ for resin infiltration, and $13.74 \mu\text{m}$ for resin infiltration + fluoride varnish. As compared with the negative control, caries inhibition was significantly greater for resin infiltration + fluoride varnish ($P < 0.05$).

In analysis comparing primary and permanent teeth, there were no statistically significant differences between groups ($P > 0.05$). There was no significant difference in Δ Z or Δ LD between primary and permanent teeth for any of the applied materials.

Table 2 Mean Δ Z and Δ LD values in each group

	Negative control	ICON	Duraphat	ICON + Duraphat
Primary teeth				
Δ Z	0.31 ± 0.12	0.14 ± 0.05	0.27 ± 0.25	0.13 ± 0.06
Δ LD	64.4 ± 0.04^a	21 ± 0.06^b	57.2 ± 0.03^a	5.78 ± 0.03^b
Permanent teeth				
Δ Z	0.23 ± 0.09	0.17 ± 0.09	0.23 ± 0.12	0.14 ± 0.08
Δ LD	56.98 ± 0.09^a	26.34 ± 0.14^a	54.8 ± 0.20^a	13.74 ± 0.09^b

Within rows, different superscript letters indicate significant differences ($P < 0.05$).

Discussion

Resin infiltration is a relatively new method for treating initial caries lesions. To our knowledge, this is the first report to use μ CT to evaluate progression of artificially induced initial caries lesions. There are several methods of measuring mineral concentrations and densities of hard dental tissues, including chemical analyses of microsamples, contact microradiography, and transversal microradiography (12). However, these methods require time and are destructive. In contrast, μ CT measures the mineral density of hard tissues such as bones and teeth, has a resolution of 5-30 μ m, and is more accurate than other methods (12,14). Because the thickness of the sample used for μ CT depends on the size of the X-ray beam, slices of the sample examined can be thinner and more regular than samples prepared by physical cutting (10).

Studies using μ CT to assess bone morphology and architecture have shown that the results correlate well with 2D histologic sections and that μ CT evaluation is thus an alternative method to nondestructive bone biopsies in analyzing 3D bone architecture (21,22).

In a comparison of the reliability of transversal microradiography and μ CT in detecting lesion depth and mineral density of caries lesions, Hamba et al. (14) showed that, when using an Al/Cu filter μ CT system, LD and ΔZ measurements correlated with those of transversal microradiography. They concluded that μ CT is preferable for studies of demineralization and remineralization, because of its nondestructive nature.

Lautensack et al. (23) reported that synchrotron X-ray μ CT yielded high-resolution images and was able to show variations in density inside the enamel structure. They concluded that quantitative image analysis methods allow for visual examination and quantification of the degree of demineralization in different samples. With μ CT, the 3D morphology of demineralization areas can be examined, which is not possible with classical 2D imaging techniques.

Oral health procedures such as brushing and flossing are recommended for patients as the first step in preventing caries lesions (24). However, Duraphat or other high-concentration fluoride methods are considered the treatment of choice for such lesions (25).

Resin infiltration is currently recommended for arresting lesion progression in non-cavitated initial caries lesions. Resin infiltration acts through capillary movement to form a barrier in the caries lesion and enhances the enamel structure, thereby preventing enamel breakdown and subsequent cavity formation. The resin used for infiltration has a high penetration coefficient, and the

enamel acts as a sponge that absorbs the infiltrant. The infiltrant completely fills the porous structure, preventing diffusion of organic acids into the lesion and inhibiting caries progression (4,5).

In our study, infiltrated lesions in primary teeth were significantly shallower than those in the negative control and fluoride groups. These findings are consistent with those of previous studies of commercially available adhesives used for sealing incipient caries lesions (6,7,26). The results of those earlier studies led to the development of the ICON material used here.

The results of an *in vitro* study of the color-masking effects of ICON showed that it was effective in masking white spot lesions and returning teeth to their natural color. However, after a new acid challenge, the resin infiltration exhibited some color changes, which suggests that some demineralization can still occur after resin infiltration treatment. Such demineralization may be caused by partial dissolution of the remaining minerals in the lesion body, which were not completely embedded within the resin matrix, or by resin shrinkage during light-curing (27).

Fluoride can remineralize incipient caries lesions at a superficial level. However, deeper segments of the enamel are more susceptible to demineralization, because the outer enamel is less soluble than the inner enamel (28-30). In the present study, we used a combination of resin infiltration with fluoride varnish to assess the effects of fluoride on remineralization. After resin infiltration, fluoride varnish was used for its remineralizing effect on the outer enamel, to provide better protection against continuous acid attacks if the resin matrix failed to infiltrate the entire lesion because of resin shrinkage.

In the present study, we compared the use of resin infiltration alone and in combination with fluoride varnish to determine whether fluoride varnish further inhibited lesion progression. Resin infiltration + fluoride varnish was better in arresting the initial lesions, as indicated by lesion depths in primary and permanent teeth. Although the difference between resin infiltration and resin infiltration + fluoride varnish was not statistically significant, the difference may still be clinically important. The absence of a statistically significant difference may have been due to the small number of samples.

Although ΔZ did not significantly differ between groups, the ranking of ΔZ values was resin infiltration + fluoride varnish < resin infiltration < fluoride varnish < negative control in primary teeth, and resin infiltration + fluoride varnish < resin infiltration < fluoride varnish = negative control in permanent teeth.

When permanent and primary teeth were compared,

there were no statistically significant differences. However, inhibition in permanent teeth was significantly greater for resin infiltration + fluoride varnish than for the negative control. In primary teeth, both resin infiltration and resin infiltration + fluoride varnish resulted in significantly shallower lesions as compared with the negative control and fluoride varnish groups. However, for resin infiltration and resin infiltration + fluoride varnish, progression of lesion depth did not significantly differ between primary and permanent teeth.

This study has some limitations. Difficulties in collecting caries-free primary teeth during exfoliation, economic constraints, and limits in access to μ CT limited the number of teeth included in the study groups and the number of scans. Although the power analysis indicated that at least five teeth should be used in each study group, a large sample of both primary and permanent teeth is needed, and further studies with larger samples are necessary.

Another limitation of the study is the degree of initial lesion depth. In this study, μ CT was performed after application of the materials. However, to standardize the procedure, μ CT scans should be obtained before and after application, to select the same degree of mineral loss and lesion depth for each sample. Future studies of ΔZ and ΔLD should be done in this manner.

In the present study, the results for ΔZ and ΔLD differed. Although change in mineral density did not significantly differ between groups, this may have been due to the above-mentioned limitations, and the numerical differences may still be clinically important. It is possible that in a study with a larger number of samples, change in mineral density would differ significantly and correlate with change in lesion depth. However, this is the first study to investigate the effects of resin infiltration, alone and in combination with a fluoride varnish, and compare the findings with those from fluoride varnish alone and a control group. Within the limitations of our study, the resin infiltration technique combined with fluoride varnish shows promise in arresting progression of initial caries lesions in primary and permanent teeth. However, the synergistic effects of the materials should be further evaluated, *in vitro* and *in vivo*, in studies with larger samples.

In conclusion, resin infiltration is a promising method for inhibiting progression of caries lesions in primary and permanent teeth, and its use in combination with fluoride products results in further inhibition. To confirm these promising findings, future studies will require larger samples and, possibly, natural lesions.

References

1. Murdoch-Kinch CA, McLean ME (2003) Minimally invasive dentistry. *J Am Dent Assoc* 134, 87-95.
2. Silverstone LM (1983) Remineralization and enamel caries: new concepts. *Dent Update* 10, 261-273.
3. Kidd EA, Joyston-Bechal S (1986) Susceptibility of natural carious lesions in enamel to an artificial caries-like attack *in vitro*. *Br Dent J* 160, 345-348.
4. Kugel G, Arsenault P, Papas A (2009) Treatment modalities for caries management, including a new resin infiltration system. *Compend Contin Educ Dent* 3, 1-10.
5. Phark JH, Duarte S Jr, Meyer-Lueckel H, Paris S (2009) Caries infiltration with resins: a novel treatment option for interproximal caries. *Compend Contin Educ Dent* 3, 13-17.
6. Mueller J, Meyer-Lueckel H, Paris S, Hopfenmuller W, Kielbassa AM (2006) Inhibition of lesion progression by the penetration of resins *in vitro*: influence of the application procedure. *Oper Dent* 31, 338-345.
7. Meyer-Lueckel H, Paris S (2008) Progression of artificial enamel caries lesions after infiltration with experimental light curing resins. *Caries Res* 42, 117-124.
8. Mellberg JR, Castrovince LA, Rotsides ID (1986) *In vivo* remineralization by a monofluorophosphate dentifrice as determined with a thin-section sandwich method. *J Dent Res* 65, 1078-1083.
9. Thomas RZ, Ruben JL, de Vries J, ten Bosch JJ, Huysmans MC (2006) Transversal wavelength-independent microradiography, a method for monitoring caries lesions over time, validated with transversal microradiography. *Caries Res* 40, 281-291.
10. Davis GR, Wong FS (1996) X-ray microtomography of bones and teeth. *Physiol Meas* 17, 121-146.
11. Schwass DR, Swain MV, Purton DG, Leichter JW (2009) A system of calibrating microtomography for use in caries research. *Caries Res* 43, 314-321.
12. Swain MV, Xue J (2009) State of the art of micro-CT applications in dental research. *Int J Oral Sci* 1, 177-188.
13. Kamburoğlu K, Kurt H, Kolsuz E, Çztas B, Tatar I, Celik HH (2011) Occlusal caries depth measurements obtained by five different imaging modalities. *J Digit Imaging* 24, 804-813.
14. Hamba H, Nikaido T, Sadr A, Nakashmai S, Tagami J (2012) Enamel lesion parameter correlations between polychromatic micro-CT and TMR. *J Dent Res* 91, 586-591.
15. Nakata K, Nikaido T, Nakashima S, Nango N, Tagami J (2012) An approach to normalizing micro-CT depth profiles of mineral density for monitoring enamel remineralization progress. *Dent Mater J* 31, 533-540.
16. Gaiser S, Deyhle H, Bunk O, White SN, Müller B (2012) Understanding nano-anatomy of healthy and carious human teeth: a prerequisite for nanodentistry. *Biointerphases* 7(1-4):4. doi: 10.1007/s13758-011-0004-8.
17. ten Cate JM, Duijsters PP (1982) Alternating demineralization and remineralization of artificial enamel lesions. *Caries Res* 16, 201-210.
18. Thaveesangpanich P, Itthagarun A, King NM, Wefel JS

- (2005) The effects of child formula toothpastes on enamel caries using two in vitro pH-cycling models. *Int Dent J* 55, 217-223.
19. Itthagarun A, King NM, Rana R (2007) Effects of child formula dentifrices on artificial caries like lesions using in vitro pH-cycling: preliminary results. *Int Dent J* 57, 307-313.
 20. Feldkamp LA, Goldstein SA, Parfitt AM, Jesion G, Kleerekoper M (1989) The direct examination of three-dimensional bone architecture in vitro by computed tomography. *J Bone Miner Res* 4, 3-11.
 21. Kuhn, JL, Goldstein SA, Feldkamp LA, Goulet RW, Jesion G (1990) Evaluation of a microcomputed tomography system to study trabecular bone structure. *J Orthop Res* 8, 833-842.
 22. Müller R, Van Campenhout H, Van Damme B, Van Der Perre G, Dequeker J, Hildebrand T et al. (1998) Morphometric analysis of human bone biopsies: a quantitative structural comparison of histological sections and micro-computed tomography. *Bone* 23, 59-66.
 23. Lautensack J, Rack A, Redenbach C, Zabler S, Fischer H, Gräber HG (2013) In situ demineralisation of human enamel studied by synchrotron-based X-ray microtomography--a descriptive pilot-study. *Micron* 44, 404-409.
 24. Hicks J, Garcia-Godoy F, Flaitz C (2003) Biological factors in dental caries: role of saliva and dental plaque in the dynamic process of demineralization and remineralization (part 1). *J Clin Pediatr Dent* 28, 47-52.
 25. Longbottom C, Ekstrand K, Zero D (2009) Traditional preventive treatment options. *Monogr Oral Sci* 21, 149-155.
 26. Paris S, Meyer-Lueckel H, Mueller J, Hummel M, Kielbassa AM (2006) Progression of sealed initial bovine enamel lesions under demineralizing conditions in vitro. *Caries Res* 40, 124-129.
 27. Rocha Gomes Torres C, Borges AB, Torres LM, Gomes IS, de Oliveira RS (2011) Effect of caries infiltration technique and fluoride therapy on the colour masking of white spot lesions. *J Dent* 39, 202-207.
 28. Theuns HM, Driessens FC, van Dijk JW, Groeneveld A (1986) Experimental evidence for a gradient in the solubility and in the rate of dissolution of human enamel. *Caries Res* 20, 24-31.
 29. Anderson P, Elliott JC (2000) Rates of mineral loss in human enamel during in vitro demineralization perpendicular and parallel to the natural surface. *Caries Res* 34, 33-40.
 30. Yamazaki H, Litman A, Margolis HC (2007) Effect of fluoride on artificial caries lesion progression and repair in human enamel: regulation of mineral deposition and dissolution under in vivo-like conditions. *Arch Oral Biol* 52, 110-120.